

IsoQure[®] DMP-30

Chemical name: Tris(dimethylaminomethyl)phenol

CAS Number: 90-72-2

EC-No. : 202-013-9

Material Definition

Appearance: Pale yellow liquid

Purity: Min. 96%

Formula: C₁₅H₂₇N₃O

Molecular weight: 265.39 g/mol

Index-No. : 603-069-00-0

Amine value: 600 to 630 mgKOH/g

Application

IsoQure[®] DMP-30 is suitable as an accelerator and hardener in epoxy resin systems, especially in the production of membranes and in pultrusion processes where reinforcement materials like fibers are first impregnated with resin and then pulled through a heated stationary die.

IsoQure[®] DMP-30 can also be used in the production of rigid polyisocyanurate foams where it acts as a delayed-action trimerization catalyst and is typically used in conjunction with other amine-based agents.

Handling, Storage and Packaging

The processing and use of IsoQure[®] DMP-30 requires adequate technical and professional knowledge. Please consult safety data sheet and observe local safety regulations. The legal requirements prevailing in your country,

especially in the avoidance of accidents, working hygiene and patent rights must be observed.

IsoQure[®] DMP-30 has to be stored in tightly sealed original containers in a cool and dry place below 28°C. Properly stored it is stable for a minimum of one year.

Safety

Avoid contact with skin and eyes. Avoid inhalation of vapour or mist. Keep container tightly closed in a dry and well-ventilated place. Containers which are opened must be carefully resealed and kept upright to prevent leakage. Storage class (TRGS 510): Combustible, corrosive hazardous materials.

Regulatory Information

EU REACH registered: No (tbd)

Availability

- Americas (United States, Canada, South America)
- APAC (Asia-Pacific)
- ANZ (Australia, New Zealand)
- EU (European Union)
- PRC (People's Republic of China)
- UK (United Kingdom)

Disclaimer / Conditions



Revision: 2020-10-28 / ef4e

We strive to be accurate in all of our documentation. However, any information or advice is provided by us in good faith, without warranty or unlimited claim of fitness for a specific application. We sell to qualified industrial users only. The onus is on the product's user to research carefully and then to continually test the product and its application procedures within the context of its specific use. Use of our products and data requires diligence and care, and is within the sole responsibility of the user. Kautschuk-Group does not accept any liability for damages incurred. Our general [Terms and Conditions \(/info/toc\)](#) apply.

Stated storage and shelf life times are minimum guaranteed values for a period starting on the day of shipment. After this period has expired, the product requires additional quality control testing but may very well still be within specification. For more information, refer to our [Shelf Life Policy \(/info/shelflife\)](#).

For updates on product information, please check this web page regularly:

<https://kautschuk.com/products/epoxy/isoquire-dmp-30>

(<https://kautschuk.com/products/epoxy/isoquire-dmp-30>)

This page is also available in: **Deutsch**

(<https://de.kautschuk.com/products/epoxy/isoquire-dmp-30>), **Español**

(<https://es.kautschuk.com/products/epoxy/isoquire-dmp-30>), **Français**

(<https://fr.kautschuk.com/products/epoxy/isoquire-dmp-30>), **简体中文**

(<https://cn.kautschuk.com/products/epoxy/isoquire-dmp-30>), **Italiano**

(<https://it.kautschuk.com/products/epoxy/isoquire-dmp-30>), **Türkçe**

(<https://tr.kautschuk.com/products/epoxy/isoquire-dmp-30>), **日本語**

(<https://jp.kautschuk.com/products/epoxy/isoquire-dmp-30>).

© 2001-2024 **Kautschuk Group** · Isochem Limited · 340 Queen's Road,
Central, · Hong Kong, SAR

For inquiries, contact: info@kautschuk.com (<mailto:info@kautschuk.com>)

[Status \(/status\)](#) · [Policies \(/info\)](#) · [Privacy \(/info/privacy\)](#) · [Terms \(/info/toc\)](#) · [Imprint \(/info/imprint\)](#)