

Isodur N3300 S

1,6-hexamethylene diisocyanate based polyisocyanate

Hexamethylene diisocyanate oligomer

CAS Number: 28182-81-2

Content: Approx. \geq 99.8

Hexamethylene-1,6-diisocyanate

CAS Number: 822-06-0

Content: Approx. $<$ 0.1

Material Definition

Appearance: Colorless to slightly yellowish clear liquid

NCO Content: 21.70 - 22.20 %

Viscosity at 25 °C: 1750 - 3250 mPa·s

Chromatic Number: \leq 40 APHA

HDI Content: $<$ 0.10 %

Application

Isodur N3300 S can be used as the hardener component for lightfast two-component polyurethane coatings with high resistance to chemicals and weathering, very good gloss retention and outstanding mechanical properties.

Preferred co-reactants are polyacrylates or polyester polyols. The main applications for coatings based on Isodur N3300 S are automotive refinishing, transportation, industrial finishing and plastics.

Handling, Storage, and Packaging

The processing and use of Isodur N3300 S requires adequate technical and professional knowledge. Please consult safety data sheet and observe local safety regulations. The legal requirements prevailing in your country, especially in the avoidance of accidents, working hygiene and patent rights must be observed.

Isodur N3300 S has to be stored in its sealed original containers at temperatures from 0 to 30°C. The product must always be kept in a sealed container as it is highly sensitive to moisture. Storage at higher temperatures may result in increasing of coloring and viscosity. Properly stored it is stable for a minimum of 15 months. If it is stored or transported at low temperatures, crystalline deposits may form but they will re-dissolve at room temperature.

Available pack sizes for Isodur RC:

- 1000kg IBC

Regulatory Information

EU REACH registered: No

Availability

- Americas (United States, Canada, South America)
- APAC (Asia-Pacific)
- ANZ (Australia, New Zealand)
- EU (European Union)
- PRC (People's Republic of China)
- UK (United Kingdom)

Disclaimer / Conditions

Revision: 2024-06-20 / 23b5



We strive to be accurate in all of our documentation. However, any information or advice is provided by us in good faith, without warranty or unlimited claim of fitness for a specific application. We sell to qualified industrial users only. The onus is on the product's user to research carefully and then to continually test the product and its application procedures within the context of its specific use. Use of our products and data requires diligence and care, and is within the sole responsibility of the user. Kautschuk-Group does not accept any liability for damages incurred. Our general [Terms and Conditions \(/info/toc\)](#) apply.

Stated storage and shelf life times are minimum guaranteed values for a

period starting on the day of shipment. After this period has expired, the product requires additional quality control testing but may very well still be within specification. For more information, refer to our [Shelf Life Policy \(/info/shelflife\)](/info/shelflife).

For updates on product information, please check this web page regularly:
<https://kautschuk.com/products/adhesives/isodur-n3300s>
(<https://kautschuk.com/products/adhesives/isodur-n3300s>)

This page is also available in: **Deutsch**
(<https://de.kautschuk.com/products/adhesives/isodur-n3300s>),
Español (<https://es.kautschuk.com/products/adhesives/isodur-n3300s>),
Français
(<https://fr.kautschuk.com/products/adhesives/isodur-n3300s>), 简体中文
(<https://cn.kautschuk.com/products/adhesives/isodur-n3300s>), **Italiano**
(<https://it.kautschuk.com/products/adhesives/isodur-n3300s>), **Türkçe**
(<https://tr.kautschuk.com/products/adhesives/isodur-n3300s>), 日本語
(<https://jp.kautschuk.com/products/adhesives/isodur-n3300s>).

© 2001-2024 Kautschuk Group · Isochem Limited · 340 Queen's Road,
Central, · Hong Kong, SAR

For inquiries, contact: info@kautschuk.com (<mailto:info@kautschuk.com>)

[Status \(/status\)](/status) · [Policies \(/info\)](/info) · [Privacy \(/info/privacy\)](/info/privacy) · [Terms \(/info/toc\)](#) · [Imprint \(/info/imprint\)](/info/imprint)